



PRODUCT DATA SUBSIC35

CHEMICAL PROPERTIES

ELEMENT	Typical %
SiC	30-40%
Free Carbon	24%
SiO ₂	34%

STANDARD SIZING

0 - 10 mm

10 - 50 mm

0 - 3.5mm

Custom sizing available



KEY PRODUCT FEATURES

SUBSIC35

- Good source of silicon
- Can be effectively used in the production of steel as a solid fuel to replace hot metal or adjust temperature.
- Has a deoxidizing effect that imparts metallurgical benefits to the metal and enhances furnace lining life.
- Reduces metal oxides in slags improving recoveries of valuable elements such as manganese and chromium.

PACKAGING

Bulk. Custom packaging available.

www.sublime-sic.com
Plot 141, Matla Power Station, P O Box 2178, Kriel, 2271
Telephone: +27 (0)17 6486016 - e-mail: info@sublime-sic.com



Product specifications are subject to change without notice